

**TEST REPORT**

Report Ref: A1523

15<sup>th</sup> October 2012

Submitted Samples: PVC Coated Fabric

Sample Reference: Veneto Range

Date Received: 9<sup>th</sup> October

Abrasion Resistance (Martindale Method)


(BS:EN:ISO 12947-2:(1999))

Pressure = 12 Kpa

End Point = A hole in the coating (backing fabric visible)

- 1) Exceeds 50,000 cycles
- 2) “ “
- 3) “ “
- 4) “ “

Mean of 4 specimens ..... Exceeds 50,000 cycles



P J Addinell